

3980 Swenson Ave
 Saint Charles, IL 60174
 630-879-9388
www.stratatac.com

PRESSURE SENSITIVE, 3.2 MIL WHITE
TYPICAL PHYSICAL PROPERTIES

<u>PROPERTY</u>		<u>VALUE</u>	<u>TEST METHOD</u>
Thickness (mils)		3.2 +/- 0.2	ASTM D- 1593
Tensile Strength (psi, min.)	MD	2900-4900	ASTM D- 882
	TD	2900-4000	
Elongation @ Break (%)	MD	70-170	ASTM D- 882
	TD	100-300	
Dimensional Stability (% change max. 150 ^o C for 30 min)	MD	-6.0 max. -5.0 target	ASTM D-1204
Gloss, Gardner 60 ^o		10 - 20 12 target	ASTM D-2457
Color Difference		1.0 max.	CIELAB
Surface Tension (dynes/cm, min.)		34	ASTM D-2578

This film is formulated without Cadmium, Phthalate plasticizers, or CONEG restricted materials.

The information in this data sheet is considered to be accurate and reliable; however, no guarantee or warranty is expressed or implied.